

AR 198

September 2018

Approval requirement 198

Multilayer piping systems for indoor gas installations



**Trust
Quality
Progress**

Foreword

This GASTEC QA approval requirement has been approved by the Board of Experts product certification GASTEC QA, in which relevant parties in the field of gas related products are represented. This Board of Experts supervises the certification activities and where necessary require the GASTEC QA approval requirement to be revised. All references to Board of Experts in this GASTEC QA Approval requirement pertain to the above mentioned Board of Experts.

This GASTEC QA approval requirement will be used by Kiwa Nederland BV in conjunction with the GASTEC QA general requirements and the KIWA regulations for product certification. This regulation details the method employed by Kiwa during product certification.

Approved by Board of Experts : 4 September 2018

Accepted by Kiwa Nederland B.V. : 4 September 2018

Kiwa Nederland B.V.

Wilmersdorf 50
Postbus 137
7300 AC Apeldoorn

Tel. 088 998 33 93
Fax 088 998 34 94
info@kiwa.nl
www.kiwa.nl

© 2017 Kiwa N.V.

All rights reserved. No part of this book may be reproduced, stored in a database or retrieval system, or published, in any form or in any way, electronically, mechanically, by print, photoprint, microfilm or any other means without prior written permission from the publisher.

The use of this evaluation guideline by third parties, for any purpose whatsoever, is only allowed after a written agreement is made with Kiwa to this end

Contents

	Foreword	1
	Contents	2
1	Introduction	3
1.1	General	3
1.2	Scope	3
2	Definitions	4
3	Product requirements	5
3.1	General	5
3.2	Pipes	5
3.2.1	Color of pipes	5
3.2.2	Outer layer of yellow pipe; Only for M-pipe	5
3.3	Fittings	5
3.3.1	Construction	5
3.3.2	Plastic fittings	5
3.3.3	Metal fittings	5
3.3.4	Installation	5
3.3.5	Transition fittings	6
3.3.6	Elastomers	6
3.4	Fitness for purpose	6
3.4.1	Diameter classes	6
4	Marking, instructions and packaging	7
4.1	Marking of the pipe	7
4.2	Marking on the fitting	7
4.3	Instructions	7
4.4	Packaging	7
5	Quality system requirements	8
6	Summary of tests	9
6.1	Test matrix	9
7	List of referenced documents and source	12
7.1	Standards / normative documents	12
7.2	Source	12

1 Introduction

1.1 General

This GASTEC QA approval requirement in combination with the GASTEC QA general requirements include all relevant requirements, which are adhered by Kiwa as the basis for the issue and maintenance of a GASTEC QA certificate for Multilayer piping systems for indoor gas installations.

This GASTEC QA Approval requirements replace the GASTEC QA Approval Requirements 198, multilayer piping systems for indoor gas installations with a maximum operating pressure up to and including 5 bar, dated 2007. And approval requirement 198-A1, Additional requirements regarding plastic fittings for multilayer pipe systems for indoor gas installations with a maximum operating pressure up to and including 5 bar, dated 2010

List of changes:

Paragraph	Change
1.1	A general introduction is included
2	A list of terms and definition is added
3	Product requirements are updated
4	A clause regarding marking, instructions and packaging is added
5	Quality system requirements are updated
6	Summary of test and inspections is updated
7	A list of relevant standards is included

1.2 Scope

This approval requirement specify the requirements for multilayer piping systems for indoor gas installations for the supply of gaseous fuels of the 2nd and 3rd family according to NEN-EN 437.

Maximum operating pressure 5 bar.

Operating temperature -20 °C up to 60 °C.

Nominal diameter up to and including 63 mm.

2 Definitions

In this approval requirement, the following terms and definitions are applicable:

Approval requirement/ Evaluation Guideline: the agreements made within the Board of Experts on the subject of certification.

Board of Experts: The Board of Experts Gastec QA.

Supplier: the party that is responsible for ensuring that the products meet and continue to meet the requirements on which the certification is based.

Manufacturer: the party that produces the product.(not necessary the supplier).

Product requirements: requirements made specific by means of measures or figures, focusing on (identifiable) characteristics of products and containing a limiting value to be achieved, which limiting value can be calculated or measured in an unequivocal manner.

Other definitions can be found in ISO 17484-1.

3 Product requirements

3.1 General

Multilayer piping systems for indoor gas installation shall meet the requirements of:
ISO 17484-1 Plastic piping systems – Multilayer pipe systems for indoor gas installations with a maximum operating pressure up to and including 5 bar (500KPa) – Part 1: Specifications for systems.

For sizes greater than 63 mm the requirements of ISO 18225 have to be fulfilled in addition

In addition the following requirements shall be met:

3.2 Pipes

3.2.1 *Color of pipes*

The outer layer of pipes shall be yellow.

3.2.2 *Outer layer of yellow pipe; Only for M-pipe*

For yellow outer layers reference materials may be used where the original pigment has been exchanged for yellow. The long term pressure strength of these materials with a new pigment shall be equal to the original reference material, according to ISO 17484, clause 5.4.1.

3.3 Fittings

The reference in ISO 17484-1 clause 6 to ISO 10838 (all parts) should be replaced by ISO 17885, Plastic piping systems – Mechanical fittings for pressure piping systems – Specification, except clause 9.3, Fitting assemblies.

The reference in ISO 17484-1 clause 6 to ISO 14531-3 should be replaced by ISO 17885, Plastic piping systems – Mechanical fittings for pressure piping systems – Specification, except clause 9.3, Fitting assemblies.

3.3.1 *Construction*

The fittings for multilayer pipes shall be able to make a mechanical connection with the multilayer pipe by pressing or clamping

3.3.2 *Plastic fittings*

Plastic body materials for fittings can be chosen from Table 1 of ISO 17885. Contrary to ISO 17885 PVDF and PPSU fittings are suitable for the use of indoor gas installations. The plastic fittings shall comply to clause 3.4 of approval requirement.

3.3.3 *Metal fittings*

Metal body material for fittings can be chosen from table 2 of ISO 17885. Other metal materials can be used if proven to meet the requirements of ISO 17885

3.3.4 *Installation*

No torn during installation on the pipe, aluminium layer and welded seam.

No damage of the pipe and fitting by use of tools and aids for installation of the fitting

Additional requirement conform ISO 17885 clause 6.6: The fitting shall not induce twisting of pipes during assembly

3.3.5 Transition fittings

Transition to other piping systems (e.g. copper, PE or steel) shall be made by one of the following methods;

1. Thread according to EN 10226-1 (or ISO 7-1).
 - a. Male thread is conical (R)
 - b. Female thread is straight (Rp)
2. Compression fitting for joining copper tubes according to approval requirement 35
3. Solder fittings (with copper tube) according to approval requirement 6

3.3.6 Elastomers

Rubber seals shall comply with EN 549 minimum temperature class A2, or EN 682 class GAL or GBL.

3.4 Fitness for purpose

3.4.1 Diameter classes

Contrary to the diameter classes in ISO 17484-1, Clause 7.1, table 2, the below defined diameter classes shall be used. These classes are used to establish the number of test samples as referred to in: ISO 17484-1, table 3: Requirements for fitness purpose of joint assemblies.

Table 1 - Diameter classes

Diameter classes	1	2	3
External diameter (mm)	$D_e < 26$	$26 \leq D_e < 40$	$40 \leq D_e \leq 63$

4 Marking, instructions and packaging

4.1 Marking of the pipe

The pipe shall be marked according to ISO 17484, but with the following modification:

- Internal fluid is not mandatory on the marking
- Gastec QA or Gastec QA logo

4.2 Marking on the fitting

The product shall be marked with the following information:

- Standard reference number
- Manufacturer or trademark
- Fluid to be conveyed or yellow marking
- Body material
- Nominal diameter(s) d_n to which the fitting is intended to joint
- Material classification of pipe(s) to which connection is permissible, including reference to pipe manufacturer
- Gastec QA or Gastec QA logo

In case it is not possible to mark the product with all aspects, it is allowed to provide the marking on the smallest package. At least the Production charge or code and manufacturer trade have to be mentioned on the fitting

4.3 Instructions

The supplier shall provide instructions. These instructions shall be in the Dutch language and describe that the product is Gastec QA certified. The instructions shall met the requirements of ISO 17484.

4.4 Packaging

The product shall be pack in such a way that contamination or damaging is not possible.

5 Quality system requirements

The supplier shall make a risk assessment of the product and production process according to chapter 3.1.1.1 and 3.1.2.1 of the GASTEC QA general requirements. The risk assessments shall be available to Kiwa for review.

6 Summary of tests

This chapter contains a summary of tests to be carried out during:

- The initial product assessment;
- The periodic product verification;

6.1 Test matrix

Description of requirement	Clause	Test within the scope of		
		Initial product assessment	Product verification	
			Verification	Frequency
Multilayer pipes for indoor gas installations				
	ISO 17484-1			
Pipes	5			
Materials	5.1			
General	5.1.1	X	X	Once a year
Reprocessable material	5.1.2	X	X	Once a year
Metallic materials	5.1.3	X	X	Once a year
General characteristics	5.2			
General	5.2.1	X	X	Once a year
Multilayer construction	5.2.2	X	X	Once a year
Minimum design coefficient	5.2.3	X		
Dimension of pipes	5.3	X	X	Once a year
Mechanical properties	5.4			
Long-term pressure strength	5.4.1	X		
Strength of the joint line of M-pipes	5.4.2	X		
Resistance to slow crack growth of the outer layer for M-pipes	5.4.3	X		
Physical properties	5.5			
General	5.5.1	X		
Additional requirements	5.5.2			
• Resistance to gas constituent	5.5.2 Table 1	X		
• Thermal durability of the outer layer of M-pipes	5.5.2 Table 1	X		
• Oxidation induction time (OIT)	5.5.2 Table 1	X		
• Delamination: P-pipes	5.5.2 Table 1	X		
• Delamination: M-pipes	5.5.2 Table 1	X		
• Odorant permeability	5.5.2 Table 1	X		

	KE 198			
Additional requirements for pipes				
Color of the pipes	3.2.1	X	X	Once a year
Outer layer of yellow pipes	3.2.2	X		
Fittings for multilayer pipes for indoor gas installations				
	ISO 17885			
Manufacturers declaration for the field application	4	X		
Materials	5			
Plastic materials	5.1	X	X	Once a year
Metal materials	5.2	X	X	Once a year
Elastomers	5.3 and/or KE 198, 3.3.6	X	X	Once a year
Lubricants and/or greases	ISO 17885, 5.4	X	X	Once a year
General characteristics	6			
Appearance	6.1	X	X	Once a year
Color	6.2	X	X	Once a year
Ultraviolet protection	6.3	X		
Threads	6.4	X	X	Once a year
Transition fittings to metal pipes	6.5	X	X	Once a year
Combined fittings	6.6	X	X	Once a year
Geometrical characteristics	7	X	X	Once a year
Physical characteristics	8			
Evaluation of the MRS value of the plastic materials	8.1	X		
Verification of long-term behavior of the plastic materials	8.2	X		
Specific material characteristics of fitting materials	8.3	X		
Application-related characteristics	8.4			
Resistance to gas constituents	8.4.2	X		
Stress corrosion resistance	8.4.2	X		
Performance requirements	9			
General	9.1	X		
Pressure resistance of the fitting body	9.2	X		
	KE 198			
Additional requirements for fittings				
Plastic fittings	3.3.2	X		
Metal fittings	3.3.3	X		
Installation	3.3.4	X	X	Once a year
Transition fittings	3.3.5	X	X	Once a year
Elastomers	3.3.6	X		

Fitness for purpose for multilayer systems for indoor use for gas installation				
	ISO 17484-1			
Requirements for the system	4			
Pressure drop	4.1	X		
Bending	4.2	X		
Corrosive conditions	4.3	X		
Fitness for purpose	7	X		
Requirements	7.2	X		
• Long-term internal pressure test	7.2 table 3	X	X	Once a year
• Tensile load 1h	7.2 table 3	X	X	Once a year
• Tensile load 800h	7.2 table 3	X		
• Joint resistance to crushing	7.2 table 3	X		
• Impact resistance of the joint	7.2 table 3	X		
• Thermal cycling resistance	7.2 table 3	X		
• Repeated bending resistance	7.2 table 3	X		
	KE 198			
Fitness for purpose	3.4			
Dimension classes	3.4.1	X		
Marking, instructions and packaging				
	KE 198			
Marking of the pipe	4.1	X	X	Once a year
Marking of the fitting	4.2	X	X	Once a year
Instructions	4.3	X	X	Once a year
Packaging	4.4	X		

In case the product or production process changes significantly a re-evaluation will be performed.

7 List of referenced documents and source

7.1 Standards / normative documents

All normative references in this Approval Requirement refer to the editions of the standards as mentioned in the list below.

EN 437: 2003+A1: 2009	Test gases- test pressure – appliance categories
EN 1333: 2006	Flanges and their joints - Pipework components - Definition and selection of PN
EN-ISO 6708: 1995	Pipe components - Definition and selection of DN (nominal size)
EN 1092-2: 1997	Flanges and their joints - Circular flanges for pipes, valves, fittings and accessories, PN designated - Part 2: Cast iron flanges
EN 14901: 2014	Ductile iron pipes, fittings and accessories - Epoxy coating (heavy duty) of ductile iron fittings and accessories - Requirements and test methods
EN 682: 2002	Elastomeric seals - Materials requirements for seals used in pipes and fittings carrying gas and hydrocarbon fluids
EN-ISO 9001: 2008 +C1: 2009	Quality management systems – Requirements
EN 10208-1: 2009	Steel pipes for pipelines for combustible fluids - Technical delivery conditions - Part 1: Pipes of requirement class A
EN-ISO 6892-1: 2009	Metallic materials – tensile testing – part 1: method at room temperature.
NEN 7231: 2011	Kunststofleidingssystemen voor gasvoorziening – hulpstukken van slagvast polyvinylchloride (slagvast PVC) – eisen en beproevingsmethoden.
EN 10226-1: 2004	Pipe threads where pressure tight joints are male on the treads – Part 1 taper external threads and parallel internal threads.
ISO 7-1: 1994+Cor 1: 2007	Pipe threads where pressure-tight joints are made on the threads - Part 1: Dimensions, tolerances and designation

7.2 Source

Parts of the text of this approval requirement have been based on ISO 17484-1 and ISO 17885.